


Origin® One Featured Materials Overview



Material Name	Categories	Ultimate Tensile Strength	Elongation at Break	Tensile Modulus	HDT	Notched Izod Impact	Partner Page
3955	●	69 MPa	2%	3786 MPa	285° C	18 J/m	LOCTITE AM
403	●	91 MPa	9%	2748 MPa	100° C	32 J/m	LOCTITE AM
3843	●	60 MPa	47%	1890 MPa	80° C	55 J/m	LOCTITE AM
3172	●	50 MPa	108%	1385 MPa	52° C	75 J/m	LOCTITE AM
ST45	●	55 MPa	16%	2000 MPa	73° C	36 J/m	BASF Forward AM
QG 500	●	20 MPa	42%	465 MPa	62° C	70 J/m	DSM Somos
402	●	5 MPa	230%	42 MPa	50° C	n/a	LOCTITE AM
EL150	●	6 MPa	150%	27 MPa	45° C	n/a	BASF Forward AM
MED412	●	38 MPa	110%	1300 MPa	40° C	43 J/m	LOCTITE AM
MED413	●	40 MPa	40%	1750 MPa	60° C	65 J/m	LOCTITE AM

Categories: ● Elastomer ● High Temp ● General Purpose ● Medical ● Tough

Stratasys Headquarters

7665 Commerce Way,
Eden Prairie, MN 55344
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

stratasys.com

ISO 9001:2015 Certified

1 Holtzman St., Science Park,
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

